



AGRI-FLEX™ 16 Bentonite

Revised: June 30, 2008
Category: Product Data Sheet

A natural sodium bentonite clay which aids pellet binding.

Typical Physical Properties *

SCREEN ANALYSIS	TYPICAL	SPECIFICATION
Dry Screen, percent plus 16 mesh	1.9	5 max
Dry Screen, percent plus 40 mesh	91.0	
Dry Screen, percent minus 70 mesh	4	10 max
Dry Screen, percent minus 200 mesh	1.3	2 max

INDUSTRIAL PROPERTIES

Moisture, percent	9	12 max
Swell Index (ml)	28	
pH - 6% suspension	9.6	
Specific Gravity	2.7	
Bulk Density (lb/ft ³) uncompacted	60	
Bulk Density (lb/ft ³) compacted	67	

- * The typical physical values listed are not to be construed as rigid specifications.
- AGRI-FLEX™ Bentonite is accepted by the Food and Drug Administration (FDA) as Generally Recognized as Safe (GRAS) as a direct food ingredient.

Bentonite Performance Minerals LLC

3000 N Sam Houston Pkwy E
Houston, TX 77032
(281) 871-7900, Fax (281) 871-7940
www.bentonite.com

Because the conditions of use of this product are beyond the seller's control, the product is sold without warranty either express or implied and upon condition that purchaser make its own test to determine the suitability for purchaser's application. Purchaser assumes all risk of use and handling of this product. This product will be replaced if defective in manufacture or packaging or if damaged. Except for such replacement, seller is not liable for any damages caused by this product or its use.

AGRI-FLEX™ is a trademark of Halliburton. © 2008 Halliburton. All Rights Reserved.