

Henbits

Gilmore City, IA

Henbits is a medium coarse particulate CaCO₃ product processed in Gilmore City, IA from quarried high calcium limestone with minimum calcium content of 38%



Particle Size Measurement -- Laser Diffraction


Average Particle Size = **2307.49** microns

Ave particle size: half of the particles are above and half are below this point on the "S" shaped cumulative distribution graph.

% Ca **39.64**
%CaCO₃ **99.10**

Typical Analyses		
Magnesium (Mg)	0.403	%
Silicon (Si)	0.09	%
Silica (SiO ₂)	0.20	%
Iron (Fe)	0.112	%
Sodium (Na)	0.017	%
Potassium (K)	0.007	%
Sulfur (S)	0.789	%
Manganese (Mn)	0.014	%
Phosphorus (P)	0.005	%
Chloride (Cl)	0.001	%
Chromium (Cr)	8	ppm
Aluminum (Al)	19	ppm
Boron (B)	10	ppm
Barium (Ba)	< 5	ppm
Lead (Pb)	< 5	ppm
Nickel (Ni)	< 5	ppm
Cobalt (Co)	< 5	ppm
Copper (Cu)	15	ppm
Zinc (Zn)	87	ppm
Cadmium (Cd)	< 5	ppm
Iodine (I)	4	ppm
Arsenic (As)	< 5	ppm
Beryllium (Be)	< 5	ppm
Selenium (Se)	0.287	ppm
Mercury (Hg)	< 0.050	ppm
Vanadium (V)	< 5	ppm
Molybdenum (Mo)	< 5	ppm
Fluorine (F)	< .10	ppm
Bismuth (Bi)	< 5	ppm
Antimony (Sb)	< 5	ppm

% Acid Solubility	
Average	39.49
Maximum	47.96
Minimum	33.51
H ₂ O	< 0.5%
Bulk Density	(lbs./cu.ft.)
Loose:	84
Packed:	94



μm = micron (1/1000 of a millimeter)

Particle Distribution--U.S.Screen Comparison			
6 X 16 mesh product			
Micron Size	U.S.Screen	% Retained	% Passing
6700	3	0.0	100.0
5600	3.5	0.0	100.0
4750	4	0.1	99.9
3350	6	3.1	96.8
2360	8	42.7	54.1
2000	10	23.2	31.0
1700	12	15.3	15.6
1180	16	12.1	3.5
850	20	1.8	1.7
425	40	0.7	1.0
75	200	0.4	0.6
	Pan	0.6	
		100.0	

cumulative distribution (laser diffraction)			
Microns	% Passing	Microns	% Passing
8750	100	525	1.07
7350	100	450	1.00
6150	100	375	0.98
5150	99.94	300	0.97
4350	99.88	250	0.95
3650	99.81	215	0.93
3050	93.74	185	0.89
2550	67.10	155	0.83
2150	39.74	130	0.77
1800	19.22	110	0.71
1500	8.37	90	0.64
1250	4.04	75	0.58
1050	2.47	65	0.54
900	1.83	55	0.52
750	1.43	45	0.44
625	1.20		