



INDUSTRIAL LIME 200
WEEPING WATER, NEBRASKA, PLANT #1
Ground Limestone
{Cross reference with Unical-P}

Chemical Analysis

<u>Element</u>	<u>Typical*/ Guaranteed</u>
Calcium (Ca)	37.74% / 33.0%
Calcium Carbonate (CaCO ₃)	94.35% / 82.5%
Calcium (Ca) Min.	33.00%
Calcium (Ca) Max.	40.00%
Moisture (%)	< 0.50%

RECOMMENDED APPLICATION

A uniform *ground limestone* powder suitable for *industrial* applications.

WET SIEVE ANALYSIS*

<u>U.S. Screen</u>	<u>% Passing</u>	<u>Average Particle Size</u>	
100	100.0	U.S. Screen	minus 200
200	93.7	Microns	10.65
325	85.3		
400	82.0		

Bulk Density*

Unpacked	62 lb/ft ³
Packed	74 lb/ft ³

* These are typical analyses and are not intended to be guarantees.

(xv)